



centro ricerche-sviluppo e laboratori prove
settori legno-arredo, ambiente e alimenti

CATAS S.p.A.
Iscr. Reg. Imprese Udine
nr. iscr. C.F. 01818850305
Reg. Impr. UD 20663
P. IVA : 01818850305
C.Soc. € 984.250,00 i.v.

Sede: Via Antica, 24/3
33048 S. Giovanni al Nat. UD
Tel. 0432.747211 r.a.
Fax 0432.747250
<http://www.catas.com>
lab@catas.com

Filiale:
Via Braille, 5
20851 Lissone MB
Tel. 039.464567
Fax 039.464565
lissone@catas.com

TEST REPORT

224284 / 1

Date received: 29/11/16

Date of test: 29/11/16

Date of issue: 07/12/16

Sample name: PELLETT SISARKA

SISARKA D.O.O.
ULICA 131, BRIGADE 12
32270 ZUPANJA
HR - CROAZIA

Determination of moisture content UNI EN ISO 18134:2015

Sampling: Carry out by the customer
Temperature: 103±2 °C
Heating period: 12 h

Test results:

N.	Moisture %
1	5,93
2	6,01
3	5,93

Mean value	5,96
-------------------	-------------

Note: The test result is reported on a wet basis.

This document is validated by digital signature and time stamping in accordance with the Italian laws and the European Directives which regulate the electronic signature systems.

Managing Director
Dr. Andrea Giavon

The sample name and, when relevant, its description, are given by the orderer, and CATAS does not assume responsibility on this matter. This test report relates to the sample submitted for the test and no others. Additions, deletions or alterations are not permitted. This test report must always be reproduced in its entirety. Unless otherwise stated, sampling has been carried out by the orderer.

TEST REPORT**224284 / 2**

Date received: 29/11/16

Date of test: 29/11/16

Date of issue: 07/12/16

Sample name: PELLETT SISARKA

SISARKA D.O.O.
ULICA 131, BRIGADE 12
32270 ZUPANJA
HR - CROAZIA**Determination of ash content EN ISO 18122:2015**

Sampling: Carry out by the customer

temperature: 550 ± 20 °C

Moisture content: 5,96 %

Apparatus: Furnace

Test result:

N.	Ash on wet basis (%)	Ash on dry basis (%)
1	0,77	0,81
2	0,78	0,83
3	0,80	0,85

Mean value	0,78	0,83
-------------------	-------------	-------------

This document is validated by digital signature and time stamping in accordance with the Italian laws and the European Directives which regulate the electronic signature systems.



Managing Director
Dr. Andrea Glavon

The sample name and, when relevant, its description, are given by the orderer, and CATAS does not assume responsibility on this matter. This test report relates to the sample submitted for the test and no others. Additions, deletions or alterations are not permitted. This test report must always be reproduced in its entirety. Unless otherwise stated, sampling has been carried out by the orderer.

TEST REPORT**224284 / 3**

Date received: 29/11/16

Date of test: 07/12/16

Date of issue: 07/12/16

Sample name: PELLETT SISARKA

SISARKA D.O.O.
ULICA 131, BRIGADE 12
32270 ZUPANJA
HR - CROAZIA**Determination of calorific value UNI EN 14918:2010**

Sampling: Carry out by the customer

Temperature: 103±2 °C per 12 ore

Apparatus: Isoperibol calorimeter.

Test result:


Moisture content: 5,96 %

N.	Gross calorific value on dry basis MJ/kg	Net calorific value on wet basis MJ/kg
1	19,85	17,3
2	20,03	17,5
3	19,66	17,1
Mean value	19,85	17,3

Note:

1 cal x 4,1868 = 1 J

This document is validated by digital signature and time stamping in accordance with the Italian laws and the European Directives which regulate the electronic signature systems.



Managing Director
Dr. Andrea Gravon

The sample name and, when relevant, its description, are given by the orderer, and CATAS does not assume responsibility on this matter. This test report relates to the sample submitted for the test and no others. Additions, deletions or alterations are not permitted. This test report must always be reproduced in its entirety. Unless otherwise stated, sampling has been carried out by the orderer.